



TECHNICAL DATA SHEET

GMUND USED

Used | 300 g/m²

Grammage	ISO 536, g/m ² :	279 - 321
Caliper	ISO 534, μm:	440 ± 25
Bulk	ISO 534, cm ³ /g:	1.5 ± 0.15
Ash	DIN 54370, %:	> 2
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2600
	length, m:	≥ 3200
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2000
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5

August, 22. 2024 DC
substitutes July 2020



TECHNICAL DATA SHEET

GMUND USED

Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

Used 0	Li 3
Used 1	Li 6
Used 2	Li 4 - 5
Used 3	Li 3
Used 4	Li 2 - 3
Used 5	Li 3
Used 6	Li 3
Used 7	Li 3
Used 8	Li 2
Used 9	Li 3 - 4
Used 10	Li 2 - 3

August, 22. 2024 DC
substitutes July 2020