



GMUND CLASSIC

Felt Blanc / Felt Crème 240 g/m²

Grammage	ISO 536, g/m²:	223 - 257
Caliper	ISO 534, μm:	350 ± 30
Bulk	ISO 534, cm³/g:	1.2 ± 0.1
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3750
	length, m:	≥ 4500
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1500
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m²:	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	o. k.





GMUND CLASSIC

Writing with ink

Micro Blanc / Leinen Blanc / Hammer Blanc 300 g/m²

Grammage	ISO 536, g/m²:	279 - 321
Caliper	ISO 534, μm:	390 ± 40
Bulk	ISO 534, cm³/g:	1.2 ± 0.1
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3750
	length, m:	≥ 4500
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1500
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5

DIN 53126: o. k.





GMUND CLASSIC

Felt Blanc / Felt Crème 320 g/m²

Grammage	ISO 536, g/m²:	298 - 342
Caliper	ISO 534, μm:	480 ± 30
Bulk	ISO 534, cm³/g:	1.2 ± 0.1
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3750
	length, m:	≥ 4500
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1800
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m²:	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	o. k.





GMUND CLASSIC

Canvas Blanc 300 g/m²

Grammage	ISO 536, g/m²:	279 - 321
Caliper	ISO 534, μm:	400 ± 30
Bulk	ISO 534, cm³/g:	1.3 ± 0.1
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3250
	length, m:	≥ 4000
	cross, m:	≥ 2500
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1500
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m²:	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	o. k.





GMUND CLASSIC

Streifen Blanc 300 g/m²

Grammage	ISO 536, g/m²:	279 - 321
Caliper	ISO 534, μm:	370 ± 30
Bulk	ISO 534, cm ³ /g:	1.2 ± 0.1
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3500
	length, m:	≥ 4000
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1500
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m²:	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	o. k.