



reacto®
CARBONLESS PAPER

reacto® CF coated front

Selbstdurchschreibepapier, Endblatt, vorderseitig gestrichen

Carbonless paper, bottom sheet, coated on the front

Papel autocopiativo, hoja final, cara recubierta

Papier autocopiant, dernière feuille, couché au recto

Merkmal Property Propiedad Caractéristique	Prüfnorm Standard Norma Norme	Einheit Unit Unidad Unité	Wert Value Valor Valeur							Toleranz Tolerance Tolerancia Tolérance
			(50)*	57	75	80	90	130	173	
Flächengewicht Basis weight Gramaje Grammage	ISO 536	g/m ² gsm	50	57	75	80	90	130	173	± 5 %
Dicke Caliper Calibre Epaisseur	ISO 534	µm	60	67	88	90	107	138	198	± 5
Glätte Bekk (OS) Smoothness Bekk (TS) Lisura Bekk anverso Lissé Bekk recto	ISO 5627	s	90	90	80	80	40	60	40	± 20
Weiß R457 Brightness R457 Blancura R457 Blancheur R457	ISO 2470	%	93	93	93	93	95	95	95	± 3
Reißlänge längs Breaking length md Longitud de rotura Longueur de rupture SM	ISO 1924-1	m	> 5.000							
Feuchte absolut Absolute humidity Humedad absoluta Humidité absolue		%	5,8							± 0,3

* nur auf Anfrage erhältlich / only available on request / disponible únicamente bajo pedido / disponible uniquement sur demande

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso / sous réserve de modifications



Koehler
PAPER

Koehler Paper SE

Hauptstraße 2 · 77704 Oberkirch · Germany · Phone +49 7802 81-0 · Fax +49 7802 81-4330 · www.koehlerpaper.com