



**reacto®**  
CARBONLESS PAPER

## reacto® CFB coated front and back

Selbstdurchschreibepapier, Mittelblatt, beidseitig gestrichen

Carbonless paper, middle sheet, coated on both sides

Papel autocopiativo, hoja intermedia, ambas caras recubiertas

Papier autocopiant, feuille intermédiaire, couché des deux côtés

| Merkmal<br>Property<br>Propiedad<br>Caractéristique                                   | Prüfnorm<br>Standard<br>Norma<br>Norme | Einheit<br>Unit<br>Unidad<br>Unité | Wert<br>Value<br>Valor<br>Valeur |    |    | Toleranz<br>Tolerance<br>Tolerancia<br>Tolérance |
|---------------------------------------------------------------------------------------|----------------------------------------|------------------------------------|----------------------------------|----|----|--------------------------------------------------|
|                                                                                       |                                        |                                    | 53                               | 60 | 75 |                                                  |
| Flächengewicht<br>Basis weight<br>Gramaje<br>Grammage                                 | ISO 536                                | g/m <sup>2</sup><br>gsm            | 53                               | 60 | 75 | ± 5 %                                            |
| Dicke<br>Caliper<br>Calibre<br>Epaisseur                                              | ISO 534                                | µm                                 | 70                               | 78 | 96 | ± 5                                              |
| Glätte Bekk (OS)<br>Smoothness Bekk (TS)<br>Lisura Bekk anverso<br>Lissé Bekk recto   | ISO 5627                               | s                                  | 45                               |    |    | ± 20                                             |
| Weiß R457<br>Brightness R457<br>Blancura R457<br>Blancheur R457                       | ISO 2470                               | %                                  | 92                               |    |    | ± 3                                              |
| Reißlänge längs<br>Breaking length md<br>Longitud de rotura<br>Longueur de rupture SM | ISO 1924-1                             | m                                  | > 5.000                          |    |    |                                                  |
| Feuchte absolut<br>Absolute humidity<br>Humedad absoluta<br>Humidité absolue          |                                        | %                                  | 5,8                              |    |    | ± 0,3                                            |

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso / sous réserve de modifications



**Koehler**  
PAPER

**Koehler Paper SE**

Hauptstraße 2 · 77704 Oberkirch · Germany · Phone +49 7802 81-0 · Fax +49 7802 81-4330 · [www.koehlerpaper.com](http://www.koehlerpaper.com)