



reacto®
CARBONLESS PAPER

reacto® CB coated back

Selbstdurchschreibepapier, Oberblatt, rückseitig gestrichen

Carbonless paper, top sheet, coated on the back

Papel autocopiativo, hoja superior, dorso recubierto

Papier autocopiant, feuille supérieure, couché au verso

Merkmal Property Propiedad Caractéristique	Prüfnorm Standard Norma Norme	Einheit Unit Unidad Unité	Wert Value Valor Valeur						Toleranz Tolerance Tolerancia Tolérance
			56	60	70	75	80	90 OCR	
Flächengewicht Basis weight Gramaje Grammage	ISO 536	g/m ² gsm	56	60	70	75	80	90	± 5 %
Dicke Caliper Calibre Epaisseur	ISO 534	µm	74	78	88	93	98	113	± 5
Glätte Bekk (OS) Smoothness Bekk (TS) Lisura Bekk anverso Lissé Bekk recto	ISO 5627	s	35						± 20
Weiße R457 Brightness R457 Blancura R457 Blancheur R457	ISO 2470	%	98	103	103	103	103	103	± 3
Opazität Opacity Opacidad Opacité	ISO 2471	%	≥ 78	≥ 79	≥ 80	≥ 82	≥ 83	≥ 85	
Reißlänge längs Breaking length md Longitud de rotura Longueur de rupture SM	ISO 1924-1	m	> 5.000						
Feuchte absolut Absolute humidity Humedad absoluta Humidité absolue		%	5,8						± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso / sous réserve de modifications



Koehler
PAPER

Koehler Paper SE

Hauptstraße 2 · 77704 Oberkirch · Germany · Phone +49 7802 81-0 · Fax +49 7802 81-4330 · www.koehlerpaper.com