

CONTACT PACK

PRODUCT DESCRIPTION

Contact Pack is a range of paper and board made with high quality virgin pulp. Optimized for use as folding boxes and cases, tags and POS materials as well as a wrap material over rigid boxes. Ideal for calendars, covers, envelopes and greeting cards. Available in White and Ivory.

Contact Pack Recycled contains 50% post-consumer waste (PCW). It is the perfect choice for sustainable packaging.



TECHNICAL DATA

THE FOLLOWING TECHNICAL DATA REFERS TO WHITE AND IVORY

	METHOD		+/-	120 g/m ²	200 g/m ²	250 g/m ²	300 g/m ²	360 g/m ²	450 g/m ²
BASIC WEIGHT	ISO 536	g/m ²	5%	120	200	250	300	360	450
THICKNESS	ISO 534	µm	5%	168	280	350	420	500	630
BULK	ISO 534	cm ³ /g	-	1,40	1,40	1,40	1,40	1,39	1,40
CIE WHITENESS*	ISO 11475	%	3	145	145	145	145	145	145
STIFFNESS MD (15°/50mm)	ISO 2493-1	mN	-	-	>80	>120	>250	>380	>700
STIFFNESS CD (15°/50mm)	ISO 2493-1	mN	-	-	>40	>60	>110	>170	>350
MOISTURE CONTENT	ISO 287	%	1,0	6,5	6,5	6,5	6,5	6,5	6,5

*Refers to White shade. The data for the 120gsm is coming soon.



RECYCLABLE



BIODEGRADABLE



ELEMENTAL
CHLORINE
FREE



ACID



SAFETY TOYS



HEAVY METAL
COMPLIANT



REACH
COMPLIANT



PAP



PAP




FSC
www.fsc.org
FSC® C001810


The mark of
responsible forestry


THE FOLLOWING DATA REFERS TO RECYCLED


	METHOD		+/-	120 g/m²	300 g/m²	360 g/m²
BASIC WEIGHT	ISO 536	g/m²	5%	120	300	360
THICKNESS	ISO 534	µm	5%	168	420	500
BULK	ISO 534	cm²/g	-	1,40	1,40	1,39
CIE WHITENESS	ISO 11475	%	3	136	136	136
STIFFNESS MD (15°/50mm)	ISO 2493-1	mN	-	-	>250	>380
STIFFNESS CD (15°/50mm)	ISO 2493-1	mN	-	-	>110	>170
MOISTURE CONTENT	ISO 287	%	1,0	6,5	6,5	6,5


Special makings are available upon request.



RECYCLABLE



BIODEGRADABLE



ECF
ELEMENTAL
CHLORINE
FREE



FREE
ACID



EN71
SAFETY TOYS



94/62
EC
HEAVY METAL
COMPLIANT


REACH
COMPLIANT


50%
SELECTED
RECYCLED
FIBRES


21
PAP


22
PAP


FSC
www.fsc.org
FSC® C001810
The mark of
responsible forestry

PRINTING AND FINISHING RECOMMENDATIONS

OFFSET PRINTING	We suggest the use of semi-fresh inks. Suitable for traditional or UV lithography. For heavier graphical objects and/or higher densities, apply enough powder. With full coverage print it is suggested to add extra desiccant and/or the use of two printing elements. Moreover, it is suggested to wash the blanket more frequently.
HP INDIGO DIGITAL PRINTING	Not suitable for HP indigo printing.
DIGITAL PRINTING	Suitable for dry toner digital printing and ink-jet printing.
SCREEN PRINTING	Suitable for screen printing.
RUNNABILITY	Suitable for embossing, punching, die cutting, creasing and hot foil stamping.
NOTE	Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapper can be opened and the paper can be used.

> Please contact our technical department for further suggestions.

MILL ACCREDITATION | Rossano Veneto VI - Italy

CORPORATE QUALITY MANAGEMENT STANDARD | UNI EN ISO 9001

ENVIRONMENTAL MANAGEMENT STANDARD | UNI EN ISO 14001

OCCUPATIONAL HEALTH AND SAFETY MANAGEMENT STANDARD | UNI EN ISO 45001

ECO-MANAGEMENT AND AUDIT SCHEME CE 1221/2009 | EMAS

We care about the environment: www.favini.com/en/sustainability