

ONE SIDE SMOOTH - ONE SIDE ROUGH GREY CARDBOARD

CARTONCINO MONOLUCIDO GRIGIO-GRIGIO

GSM	THICKNESS	BULK	TABER STIFFNESS 15°	
Grammatura	Spessore	Volume	Rigidità Taber 15°	
			Longitudinal	Transversal
g/mq	mm	cm3	MD	CD
350	0.55	1.55	300	100
450	0.66	1.48	390	130
500	0.74	1.48	460	160
550	0.81	1.48	600	220
600	0.89	1.48	1000	380
650	0.96	1.48	1100	430
700	1.04	1.49	1200	520
750	1.12	1.49	1310	590
800	1.19	1.49	1410	650
850	1.27	1.49	1580	750
900	1.35	1.49	1680	860
950	1.42	1.50	1700	980
1000	1.50	1.50	1750	1000

TOLERANCES

Tolleranze

GSM	+/- 5%
MOISTURE 6,5%	+/- 1%
THICKNESS	+/- 5%
STIFFNESS	+/- 10%