

Scheda Tecnica

Picasso



Grammatura <i>Tolleranza</i>	ISO 536	g/m ²	95	120 ±6%	145 ±6,5%	260 ±7%	320 ±7%
Spessore <i>Tolleranza</i>	ISO 534	µm	137	172 ±6,5%	208 ±7%	375 ±7,5%	464 ±7,5%
Luminosità UV	ISO 2470	%	73,5	73,5	73,5	73,5	73,5
Opacità	ISO 534	%	90	92	94	-	-
Lunghezza rottura DL	ISO 1924	km	5,4	5,2	5,2	4,5	-
Lunghezza rottura DT	ISO 1924	km	2,9	2,8	2,8	2,4	-
Rigidità Long.	ISO 2493	mN	8,5	20	29	165	300
Rigidità Trasv.	ISO 2493	mN	4,3	10	14	76	145
Codice di riciclo		PAP	22	22	22	21	21



Il marchio della
gestione forestale
responsabile

Gennaio 2025